



COMMERCIAL

# Silento 50

## Heterogeneous Vinyl

### Technical Specifications

Spécifications techniques - Technische specificaties - Technische Specificationen

<b>Flooring type</b> / Type de couverture - Type vloer - Fußbodenart		Acoustic Flooring
<b>Heterogeneous PVC</b> / PVC hétérogène - Heterogene PVC - Heterogene PVC	EN ISO 11638	
<b>Type of installation</b> / Type de pose - Type installatie - Art der Installation		Glued
<b>Level of use</b> / Classe d'usage - Gebruiksklasse - Eignungsklasse	EN ISO 10874	23 - 33
<b>Total thickness</b> / Epaisseur totale - Totale dikte - Gesamtdicke	EN ISO 24346	3,00 mm
<b>Wear layer</b> / Couche d'usure - Slijtlaag - Nutzschiicht	EN ISO 24340	0,50 mm
<b>Wear layer PUR treatment</b> / Traitement polyuréthane - PUR slijtlaag behandeling - Schutz vor Schmutz PUR		HyperGuard+
<b>Total weight/m<sup>2</sup></b> / Poids total/m <sup>2</sup> - Totaal gewicht/m <sup>2</sup> - Gewicht/m <sup>2</sup>	EN ISO 23997	ca. 2.198 g
<b>Width</b> / Largeur - Breedte - Breite	EN ISO 24341	2-4 m
<b>Standard Length</b> / Longueur standard - Standaardlengte - Standardlänge	EN ISO 24341	ca. 25 m
<b>Weight of standard roll</b> / Poids standard des rouleaux - Standaard rolgewicht - Standard-Rollengewicht		ca. 114 - 228 kg
<b>Inflammability</b> / Classement feu - Brandklasse - Brandverhalten	EN 13501	Bfl-S1*
<b>Slip resistance</b> / Glissance - Antislip - Rutschfest	EN 13893	DS
<b>Slip restraint</b> / Résistance au glissement - Slipweerstand - Rutschhemmung	EN 16165 Annex B	R9
<b>Residual indentation</b> / Poinçonnement rémanent - Restindruk - Eindrückverhalten Average value / valeur moyenne - gemiddelde waarde - Durchschnittswert	EN ISO 24343-1	norm ≤ 0,20 mm 0,16 mm
<b>Furniture leg resistance</b> / Résistance au pied de meuble - Meubelpoottest - Möbelschubtest	EN ISO 16581	PASS
<b>Curling</b> / Incurvation - Krulling - Schüsselung	EN ISO 23999	≤ 8 mm
<b>Electrical resistance</b> / Résistance électrique - Elektrische weerstand - Elektrischer Widerstand	EN 1081	1,32 x 10 <sup>8</sup> Ohm
<b>Static electrical propensity</b> / Accumulation de charges électrostatiques - Electrostatistische Propensiteit - Elektrostatistische Verhaltung	EN 1815	≤ 2kV (antistatic)
<b>Dimensional stability</b> / Stabilité dimensionnelle - Dimensionale stabilität - Massänderung Average value / valeur moyenne - gemiddelde waarde - Durchschnittswert	EN ISO 23999	norm ≤ 0,40% 0,05%
<b>Thermal conductivity</b> / Conductivité thermique - Warmtedoorgangscoefficient - Wärmeleitfähigkeit	EN 12667	0,083 W/(m.K)
<b>Heat insulation</b> / Isolation thermique - Thermische isolatie - Wärmedurchlasswiderstand	EN 12667	0,0336 (m <sup>2</sup> .K/W)
<b>Binder quantity in wear layer</b> / Taux de liant dans la couche d'usure - Hoeveelheid bindmiddel in slijtlaag - Bindemittelmengde in der Nutzschiicht	EN 11638	Type I
<b>Abrasion group</b> / Groupe d'abrasion - Slijtageweerstand - Verschleißverhalten	EN 660-2	Class T
<b>Indoor air quality</b> / Qualité de l'air intérieur - Binnenmilieu - Raumluftqualität		LOW VOC
<b>Acoustic insulation</b> / Efficacité acoustique - Kontaktgeluidisolatie - Trittschallverbesserungsmaß	EN ISO 717-2	ΔLw 18 dB
<b>Castor chair resistance</b> / Résistance aux chaises à roulettes - Bestand tegen stoelwielen - Stuhlrollenfestigkeit	EN ISO 4918	PASS
<b>Castor type</b> / Type de chaises à roulettes - Type stoelwielen - Stuhlrolle Typ	EN 12529	Type W
<b>Light fastness</b> / Résistance à la lumière - Lichtechtheid - Lichtecheit	ISO 105-B02	≥ 6
<b>Underfloor heating</b> / Chauffage par le sol - Vloerverwarming - Bodenheizung	EN 12524	Suitable ≤ 27°C
<b>Resistance to chemicals</b> / Résistance aux produits chimiques - Chemicaliënresistentie - Chemikalienbeständigkeit	EN ISO 26987	Very good
<b>Hot welding</b> / Soudure thermique - Warm lassen - Thermische Verschweißung		Available
<b>Cold welding</b> / Soudure à froid - Koud lassen - Kaltverschweißung	Invisiweld	Suitable
<b>Warranty years</b> / Durée de la garantie en années - Garantie in jaren - Garantie Jahren		7

\*Tested on concrete subfloor (Cfl-S1 on wood).

The warranty covers manufacturing defects and premature wear in the event of normal use. The products do not contain any substances from the current candidate list published by ECHA (substances of very high concern) to be published under the REACH regulation. Exclude any rubber parts that may come into direct contact with the flooring (chair ends, furniture, wheels). Use only PVC or polyethylene components. IVC reserves the right to change or amend any written information without notice. Ensure the latest information is being consulted by referring to the website.



INSTALL AND CLEAN